

Uddeholm Dievar®

Premium Hot Work Die Steel

	Vacuum	/	Atmosphere Furnace Muffle Furnace / Packed	Salt Bath** / Fluidized Bed												
	** Salt Bath heat treatment can be performed but is not recommended for details with blind holes or threaded holes that will not be rework after heat treatment.															
Preheating Temperature	Blocks < 12" thick 1. Bring up to 1200°F, equalize 2. Heat up to 1500°F, equalize		Blocks > 12" thick 1. Bring up to 1100-1200°F, equalize 2. Heat up to 1510°F, equalize 3. Heat up to 1650°F, equalize	1. 800-900°F, equalize 2. 1100 – 1200°F, equalize 3. 1500 – 1500°F, equalize Step 1 only for big blocks (cross section above 6")												
Hardening Temperature (Austenitizing)	1830 - 1875°F (Normally 1850°F) For dies 6-12" in cross section 1850-1870°F is recommended; if greater than 12" in cross section 1830°F is recommended. Holding time after the tool or part has fully heated through at the hardening temperature: minimum 30 minutes, maximum 1 hour. Alternatively hold 20 minutes for first 1" and then 15 minutes for each additional inch of wall thickness.															
Quenching *	Alt. 1 Inert gas, positive pressure Alt. 2 Back-filled pressurized gas 610-840°F, then equalize center and surface (maximum holding time 30 minutes). Continue forced cooling to 150°F.		Alt. 1 Quench in oil 175°F until the die is black Alt. 2 Martempering, salt bath or fluidized bed at 840-1020°F or 360-390°F	Alt. 1 Oil 175°F until the die is black, then air cool Alt. 2 Circulated high speed inert gas												
	*Cooling rate must be adequate to avoid any transformation products, with decreased properties as a result. However, also consider the risk of excessive distortion from very fast cooling. A minimum quench rate of 50°F/minute as measured at a depth of ~5/8" is recommended to optimize tool properties.															
Tempering (minimum two times) Temper immediately after quenching when the complete tool reaches 150°F	Hardening Temperature: 1850 °F		<table border="0"> <thead> <tr> <th><u>Tempering Temperatures</u></th> <th><u>Hardness</u></th> </tr> </thead> <tbody> <tr> <td>1050 °F</td> <td>48-52 HRC</td> </tr> <tr> <td>1070 °F</td> <td>46-50 HRC</td> </tr> <tr> <td>1090 °F</td> <td>44-48 HRC</td> </tr> <tr> <td>1125 °F</td> <td>42-46 HRC</td> </tr> <tr> <td>1150 °F</td> <td>40-44 HRC</td> </tr> </tbody> </table>		<u>Tempering Temperatures</u>	<u>Hardness</u>	1050 °F	48-52 HRC	1070 °F	46-50 HRC	1090 °F	44-48 HRC	1125 °F	42-46 HRC	1150 °F	40-44 HRC
<u>Tempering Temperatures</u>	<u>Hardness</u>															
1050 °F	48-52 HRC															
1070 °F	46-50 HRC															
1090 °F	44-48 HRC															
1125 °F	42-46 HRC															
1150 °F	40-44 HRC															
	Times: 1 hour per inch of wall thickness, or hold at temperature a minimum of 2 hours. Check hardness between tempers.															
Stress Temper performed on hardened tools after EDM, welding with QRO 90 or DIEVAR TIG Rods, or during preventative maintenance	Check hardness to confirm tool status. Temperature: Shall be 50°F (28°C) below the lowest tempering temperature. Time: Soak 30 minutes per inch of maximum section with a minimum of 2 hours once tool comes to temperature. Cool in still air for simple shapes. For complex shapes, furnace cool to 800°F, then air cool.															
Dimensional Stability	Average size change as a result of hardening and tempering may not exceed 0.005 inch/inch/maximum dimension if the tool has been stress relieved before finish machining. If stress relieving is not performed as recommended, dimensional stability may be inconsistent and cannot be guaranteed.															
The generally recommended hardness ranges for the following hot work tool steels in die casting applications are as follows if there are no gross cracking issues:																
	<u>ORVAR SUPERIOR</u>		<u>DIEVAR</u>													
Die parts < 5" thick	46-48 HRC		47-52 HRC													
Die parts 5-9" thick	44-46 HRC		45-47 HRC													
Die parts > 9-12"	42-44 HRC		43-45 HRC													
Die parts > 12-16"	40-42 HRC		41-43 HRC													
Die parts > 16"	Per Application															

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be construed as a warranty of specific properties of the products described or a warranty for fitness for a particular purpose. It is your responsibility to confirm you have the latest revision of this document (verify on our website) and that you forward to your Heat Treatment service provider. Failure to do so may result in inferior material properties. Revision Date: June 5, 2018